

| TEST REPORT Primary batteries EN IEC 60086-1 – Part 1: General & EN IEC 60086-2 – Part 2: Physical and electrical specifications | |
|---|--|
| Report Reference No..... | 2404B0730SHA-016 |
| Tested by (name + signature)..... | Michael Zheng <i>Michael Zheng</i> |
| Approved by (name + signature) | Liping Chen <i>Liping Chen</i> |
| Date of issue | 2024-11-15 |
| Testing Laboratory | Intertek Testing Services (Shanghai FTZ) Co., Ltd. |
| Address..... | Building No.86, 1198 Qinzhou Road (North), Shanghai 200233, China |
| Testing location/procedure | <input checked="" type="checkbox"/> TL <input type="checkbox"/> RMT <input type="checkbox"/> SMT <input type="checkbox"/> WMP <input type="checkbox"/> TMP |
| Address..... | Same as above |
| Applicant's name | Zhejiang Mustang Battery Co., Ltd. |
| Address..... | No.818 Rongji Road, Luotuo Town, Ningbo, China 315202 |
| Test specification: | |
| Standard | EN IEC 60086-1: 2021+AC:2022-07; EN IEC 60086-2: 2021+AC:2022-07 |
| Test procedure..... | Testing |
| Non-standard test method..... | N/A |
| Test item description | Extra Alkaline Battery |
| Trade Mark | Raymax |
| Model and/or type reference..... | LR6 (AA) |
| Manufacturer | Zhejiang Mustang Battery Co., Ltd. No.818 Rongji Road, Luotuo Town, Ningbo, China 315202 |
| Rating(s) | 1.5V |
| Expiration Date | Marked 04-2029 on battery bottom |
| Date Received | 2024-05-19 |
| Date Test Conducted..... | 2024-06-06 to 2024-07-25 |
| Test Result | Pass |

- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

| EN IEC 60086-1 – Part 1: General | | |
|--|---|----------------|
| Requirements | Result – Remark | Verdict |
| <p>Clause 1: Scope This part of EN IEC 60086 is intended to standardize primary batteries with respect to dimensions, nomenclature, terminal configurations, markings, test methods, typical performance, safety and environmental aspects. The object of this part of EN IEC 60086-1 is to benefit primary battery users, device designers and battery manufacturers by ensuring that batteries from different manufacturers are interchangeable according to standard form, fit and function. Furthermore, to ensure compliance with the above, this part specifies standard test methods for testing primary cells and batteries</p> | Alkaline Zinc Manganese Dioxide Battery | Pass |
| <p>Clause 2: Normative references EN IEC 60086-2, Primary batteries – Part 2: Physical and electrical specifications EN IEC 60086-3, Primary batteries – Part 3: Watch batteries EN IEC 60086-4, Primary batteries – Part 4: Safety of lithium batteries EN IEC 60086-5, Primary batteries – Part 5: Safety of batteries with aqueous electrolyte</p> | | Pass |
| <p>Clause 3: Terms and definitions</p> | | Pass |
| <p>Clause 4: Requirements</p> | | Pass |
| <p>Clause 4.1: General (Design, Battery dimensions, Terminals, Classification, Designation, Marking)</p> | Dimension see table 1; Batteries are marked on intermediate package with IEC designation “LR6, marked on battery body with common designation “AA”. Polarity “+” and “-”, nominal voltage “1.5V”, trademark “Raymax”, battery expiration date “04-2029” marked on battery bottom. Caution advice also marked on both battery body and intermediate package. | Pass |
| <p>Clause 4.1.3.2: Contact pressure resistance</p> | A force of 10 N applied through a steel ball of 1 mm diameter at the centre of each contact area for a period of 10 s shall not cause any apparent deformation which might prevent satisfactory operation of the battery. | Pass |
| <p>Clause 4.2: Performance (Discharge performance, Dimensional stability, Leakage, Open-circuit voltage limits, Service output, Safety)</p> | See table 1 and 2 | Pass |

- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

| | | |
|--|---------------------------|------|
| Clause 5: Performance – Testing (Discharge testing, include Application tests and Service output tests, OCV testing, Battery dimensions, Leakage and deformation- closed circuit voltage drops for the first time below 40 % of the nominal voltage of the battery) | See table 2 | Pass |
| Clause 6: Performance – Test conditions | | N/A |
| Clause 7: Sampling and quality assurance | Samples selected randomly | Pass |
| Clause 8 Battery packaging | | N/A |
| Annex A (normative): Criteria for the standardization of batteries | | Pass |
| Annex B (informative): Recommendations for equipment design | | N/A |
| Annex C (normative): Designation system (nomenclature) | | Pass |
| Annex D (informative): Standard discharge voltage Us – Definition and method of determination | | N/A |
| Annex E (informative): Preparation of standard methods of measuring performance (SMMP) of consumer goods | | N/A |
| Annex F (informative): Guidance for proposing value of minimum average duration | | N/A |
| Annex G (normative): Code of practice for packaging, shipment, storage, use and disposal of primary batteries | | N/A |
| Annex H (informative): Compliance checklist | | N/A |


- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

| EN IEC 60086-2 – Part 2: Physical and electrical specifications | | |
|---|---|----------------|
| Requirements | Result – Remark | Verdict |
| <u>Clause 1: Scope</u> This part of EN IEC 60086 is applicable to primary batteries based on standardized electrochemical systems. It specifies – the physical dimensions, – the discharge test conditions and discharge performance requirements. | Alkaline Zinc Manganese Dioxide Battery | Pass |
| <u>Clause 2: Normative references</u> EN IEC 60086-1, Primary batteries – Part 1: General; ISO 1101, Geometrical product specifications (GPS) – Geometrical tolerancing – Tolerances of form, orientation, location and run-out | | Pass |
| <u>Clause 3: Terms, definitions, symbols and abbreviations</u> | | Pass |
| <u>Clause 4: Battery dimensions, symbols</u> | | Pass |
| <u>Clause 5: Dimensional stability</u> | | Pass |
| <u>Clause 6: Validity of testing</u> | | Pass |
| <u>Clause 7: Constitution of the battery specification tables</u> | Classified as “LR6”. | Pass |
| <u>Clause 8: Physical and electrical specifications</u> | | N/A |
| <u>Annex A (informative):</u> Tabulation of batteries by application | LR6: 1.5V; | Pass |
| <u>Annex B (informative):</u> Cross-reference index | Category 1 batteries: LR6 | Pass |
| <u>Annex C (informative):</u> Index | | Pass |
| <u>Annex D (informative):</u> Common designation | LR6 (Common Designation: AA) | Pass |
| <u>Annex E (informative):</u> Compliance checklist | | N/A |

- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

Table 1: Dimensions

This was conducted in accordance with an application test stated in IEC/EN 60086-1/-2.
The battery required to meet the dimensions, which was shown below:



h_1 maximum overall height of the battery;
 h_2 minimum distance between the flats of the positive and negative contacts;
 h_3 minimum projection of the flat positive contact;
 h_4 maximum recess of the negative flat contact surface;
 d_1 maximum and minimum diameters of the battery;
 d_3 maximum diameter of the positive contact within the specified projection height;
 d_6 minimum outer diameter of the negative flat contact surface;
 $\varnothing P$ concentricity of the positive contact.

| Dimensions | | LR6 |
|-----------------|------|------|
| h_1 | max. | 50,5 |
| h_2 | min. | 49,5 |
| h_3 | min. | 1,0 |
| h_4 | max. | 0,5 |
| d_1 | max. | 14,5 |
| | min. | 13,7 |
| d_3 | max. | 5,5 |
| d_6 | min. | 7,0 |
| $\varnothing P$ | max. | 0,25 |

Table 1: Dimensions and OCV measurement (continued)

| Designation | Open circuit voltage (V) | Dimensions (mm) | | | | | | | | |
|-------------|--------------------------|-----------------|-------|-------|-------|-------|------|-------|-------|-----------------|
| | | h_1 | h_2 | h_3 | h_4 | d_1 | | d_3 | d_6 | $\varnothing P$ |
| LR6 (AA) | Max. | Max. | Min. | Min. | Max. | Max. | Min. | Max. | Min. | Max. |
| | 1.68 | 50.5 | 49.5 | 1.0 | 0.5 | 14.5 | 13.7 | 5.5 | 7.0 | 0.25 |

| Sample no. | | | | | | | | | |
|------------------------|---------------|---------------|-------------|----------------|---------------|-------------|-------------|-------------|------|
| All samples under test | 1.625 ~ 1.632 | 50.19 ~ 50.25 | 1.60 ~ 1.66 | - | 14.11 ~ 14.15 | 5.21 ~ 5.26 | 9.02 ~ 9.07 | 0.11 ~ 0.12 | |
| Verdict | Pass | Pass | Pass | Not applicable | Pass | Pass | Pass | Pass | Pass |

- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

Table 2: Discharge / Application Tests and leakage and deformation check

Designation: LR6 (AA)

Manufacturing date: 2022-02

| | | | | | | |
|---------------|-------------------------|--------------------|------------|--------------------------------|--|--------------------------------------|
| Application: | Portable lighting (LED) | Toy, non-motorized | Motor/ Toy | Radio / Clock / Remote Control | CD, digital audio, wireless gaming and accessories | High drain application |
| Load: | 3.9 Ω | 250 mA | 3.9 Ω | 50 mA | 100 mA | 1500mW 650mW 0mW |
| Daily period: | 4 min / h, 8 h / d | 1 h / d | 1 h / d | 1 h / 8 h, 24 h / d | 1 h / d | 1.5W2S/0.65 W28S, 10t/h, 24h/d |
| EV: (V) | 0.9 V | 0.9 V | 0.8 V | 1.0 V | 0.9 V | 1.05V |
| MAD: | 230 min | 5 h | 5 h | 30 h | 15 h | 40 pulses |

Test result:

| Sample no. | | | | | | |
|-------------------|----------------|----------------|----------------|----------------|----------------|----------------|
| 1 | 439.4 min | 8.6 h | 8.4 h | 51.5 h | 24.4 h | 118 |
| 2 | 438.6 min | 8.6 h | 7.9 h | 51.9 h | 24.6 h | 117 |
| 3 | 443.2 min | 8.5 h | 8.0 h | 52.3 h | 24.5 h | 117 |
| 4 | 442.7 min | 8.6 h | 8.4 h | 51.5 h | 24.6 h | 117 |
| 5 | 438.8 min | 8.6 h | 8.4 h | 51.5 h | 24.6 h | 119 |
| 6 | 442.2 min | 8.6 h | 8.0 h | 51.5 h | 24.6 h | 119 |
| 7 | 439.7 min | 8.6 h | 8.0 h | 51.5 h | 24.6 h | 108 |
| 8 | 439.6 min | 8.6 h | 8.4 h | 51.6 h | 24.6 h | 117 |
| Average | 440.5 min | 8.6 h | 8.2 h | 51.7 h | 24.6 h | 117 |
| Verdict | Pass | Pass | Pass | Pass | Pass | Pass |
| Leakage check | No leakage |
| Deformation check | No deformation |

- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.

Product Photos:

LR6 (AA)



- The test results reported in this test report shall refer only to the sample actually tested and shall not refer or be deemed to refer to bulk from which such a sample may be said to have been obtained.
- This report shall not be reproduced except in full without prior authorization from Intertek Testing Services Shanghai.
- The services are provided subject to the terms and condition of the company, which can be furnished upon request.
- Throughout this report a point is used as the decimal separator.