



nanotech REVOLUTION

Date of issue 20.05.2023

Page 1 of 1

PRODUCT SPECIFICATION

Maskinstrekkfilm NOR REVOLUTION 10my

Doc. No. SPEC-2501-121V1

Physical Properties	Test Method	Value	Unit
Width	Measurement Tape	500 (+/-5)	mm
Average Thickness	Thickness Gauge	(0.010) +/-0.001	mm
Ultimate Stretch Level	Testing Method	> 330	%
Quality Test	Testing Method	Pass	Stretch at 250% Continuous run 50 meter
Tensile Strength	ASTM D 882	MD \geq 28 TD \geq 17	MPa
Elongation	ASTM D 882	MD \geq 370 TD \geq 460	%
Dart Impact	ASTM D 1709	\geq 100	gm
Tear Strength	ASTM D 1922	MD \geq 75 TD \geq 345	gm

Unless otherwise agreed in writing, we sell products without warranty, and buyers and users assume all responsibility and liability for loss or damage arising from the handling and use of our products, whether used alone or in combination with other products.

Prepared by:

Reviewed by:

Approved by: